

Garnet®

High hardness and high density granular filter media

Called multi-media or mixed media filtration, the high density, small grain size of Clack #30-40 Garnet solves a major filtration problem. In a single media granular filter such as a sand filter, the material will hydraulically classify during backwash according to granule size, the smallest rising to the top. When water flows downward through the sand, the fine particles at the top of the bed do most of the straining of the sediment. The solids form a cake on the surface with filtration typically taking place in the top few inches. As the cake forms, the filtration becomes finer and the head loss increases exponentially with time.

The ideal situation would be to have the large grains of media at the top to trap the large solids, and a uniformly decreasing grain size in the direction of fluid flow with the small grains at the bottom to do the final polishing. The penetration of the solids into the entire bed allows for increases solids storage, longer filter runs, and higher filtration rates.

A properly designed multi-media system will maintain its unique grading of large grains on the top and small grains on the bottom and provide superior performance even after many backwashings. This stable condition of large grains above finer ones is achieved by the use of materials of different sizes and specific gravities. Garnet with its high specific gravity of 4.0 forms the lower fine grain layer, its 0.3 mm effective size can filter down to the 10-20 micron range. Filter Sand, (effective size of 0.9 mm), or Filter Ag[®] can form the larger, less dense layers.

Multi-media filtration technology is applicable to both water and waste water treatment. Custom designed filters with varying filter bed configurations can be designed to meet specific needs. For the majority of municipal and industrial water supply applications, a filter bed composed of 55% low density material, 30% medium density material, and 15% high density material is recommended.

#8 Garnet at 140 lb/ft³ is a good choice for support beds when using other high density filtration media such as high purity Corosex II or the new manganese dioxide oxidation medias such as Pyrolox.



ADVANTAGES

- High specific gravity allows unique filter design
- In combination with other filter medias, higher flow rates, higher loading and better filtration can be achieved
- High hardness reduces attrition and provides for years of reliable service
- An excellent support bed for other high density medias
- Clack garnet meets AWWA B100-96 specifications


PHYSICAL PROPERTIES

Color:	Light tan to reddish purple		
Type:	Almandite		
Crystal System:	Cubic		
Hardness:	7.0-7.5 (Mohs scale)		
Bulk Density:	#8 Garnet:	2,25 kg/dm ³	
	#8-12 Garnet:	2,25 kg/dm ³ .	
	#30-40 Garnet:	2,1 kg/dm ³	
Effective Size:	#8 Garnet:	2.0 mm	
	#8-12 Garnet:	1.5 mm	
	#30-40 Garnet:	0.35 mm	
Uniformity Coefficient:	#8 Garnet:	1.3	
	#8-12 Garnet:	>1.5	
	#30-40 Garnet:	1.4	
Specific Gravity:	3.8-4.2 gm/cc		
Free Silica:	Minimal		
Acid Solubility:	Minimal		


CONDITIONS FOR OPERATION

Wide range – application specific

Pressure drop (bars per m bed depth)



Bettexpansion in %



Garnet® is a federally registered trademark of Clack Corporation WS / USA

Garnet® is tested and listed under ANSI / NSF and classified by UL INC. as drinking water treatment system components acc. to ANSI/NSF 61-(1991)-57Y3

Packing : 28,3 Liter (1 ft³) Säcke

Distributed by :

INAQUA Vertriebsgesellschaft mbH

Langmaar 7

D-41238 Mönchengladbach

Tel.: 02166 - 62199 - 0

Fax : 02166 - 62199 - 26

website:www.inaqua.de



The information and recommendation in this publication are based on data we believe to be reliable. They are offered in good faith, but do not imply any warranty or performance guarantee, as conditions and methods of use of the products are beyond our control. Original brochures are valid. Specifications are subject to change without notice.