



AMBERLITE® IRC86

Industrial Grade Strong Acid Exchanger

PRODUCT DATA SHEET

AMBERLITE IRC86 is a high capacity weak acid cation exchange resin containing carboxylic acid groups. It is characterised by an outstanding physical and chemical stability. Its principal application is the dealkalisation of industrial waters. AMBERLITE IRC86, in the hydrogen cycle, removes hardness associated with alkalinity. Combined with a strong acid cation exchanger, it allows to reduce acid consumption

in deionisation. Due to its high swelling between H^+ and Na^+ or NH_4^+ forms, it is recommended not to use AMBERLITE IRC86 between these ionic forms.

The presence of chlorine in the water to be treated does not affect the performance of the resin.

PROPERTIES

Matrix _____	Gel polyacrylic copolymer
Functional groups _____	- COO^-
Physical form _____	Clear yellow beads
Ionic form as shipped _____	H^+
Total exchange capacity ^[1] _____	≥ 4.10 eq/L (H^+ form)
Moisture holding capacity ^[1] _____	47 to 53 % (H^+ form)
Specific gravity _____	1.17 to 1.195 (H^+ form)
Shipping weight _____	790 g/L
Particle size _____	
Harmonic mean size _____	0.580 - 0.780 mm
Uniformity coefficient _____	≤ 1.80
Fine contents ^[1] _____	< 0.300 mm : 2.0 % max
Coarse beads _____	> 1.180 mm : 5.0 % max
Maximum reversible swelling _____	$H^+ \rightarrow Na^+$: 100 %
(total conversion)	$H^+ \rightarrow Ca^{++}$: 15 %
	$H^+ \rightarrow Mg^{++}$: 50 %

^[1] Contractual value

Test methods are available on request.

SUGGESTED OPERATING CONDITIONS

Maximum operating temperature _____	120°C
Minimum bed depth _____	700 mm
Service flow rate _____	5 to 70 BV*/h
Regenerant _____	HCl H_2SO_4
Flow rate (BV/h) _____	2 to 8 15 to 40
Concentration (%) _____	2 to 5 0.5 to 0.7
Level _____	104 to 110 % of ionic load
Minimum contact time _____	30 minutes
Slow rinse _____	2 BV at regeneration flow rate
Fast rinse _____	2 to 4 BV at service flow rate

* 1 BV (Bed Volume) = 1 m^3 solution per m^3 resin

PERFORMANCE

The operating capacity of AMBERLITE IRC86 is a function of analysis, temperature and service flow rate of water. Data providing information to calculate the capacity are given in the engineering data sheet (EDS 0235 A).

LIMITS OF USE

AMBERLITE IRC86 is suitable for industrial uses. For all other specific applications such as pharmaceutical, food processing or potable water applications, it is recommended that all potential users seek advice from Rohm and

Haas in order to determine the best resin choice and optimum operating conditions.

HYDRAULIC CHARACTERISTICS

Figure 1 shows the bed expansion of AMBERLITE IRC86 as a function of backwash flow rate and water temperature.

Figure 2 shows the pressure drop data for AMBERLITE IRC86, as a function of service flow rate and water temperature. Pressure drop data are valid at the start of the service run with a clear water and a correctly classified bed.

Figure 1: Bed Expansion





Figure 2: Pressure Drop



All our products are produced in ISO 9002 certified manufacturing facilities.

Rohm and Haas/Ion Exchange Resins - Philadelphia, PA - Tel. (800) RH AMBER - Fax: (215) 537-4157
Rohm and Haas/Ion Exchange Resins - 75579 Paris Cedex 12 - Tel. (33) 1 40 02 50 00 - Fax : 1 43 45 28 19

WEB SITE: <http://www.rohmhaas.com/ionexchange>



AMBERLITE is a trademark of Rohm and Haas Company, Philadelphia, U.S.A.

Ion exchange resins and polymeric adsorbents, as produced, contain by-products resulting from the manufacturing process. The user must determine the extent to which organic by-products must be removed for any particular use and establish techniques to assure that the appropriate level of purity is achieved for that use. The user must ensure compliance with all prudent safety standards and regulatory requirements governing the application. Except where specifically otherwise stated, Rohm and Haas Company does not recommend its ion exchange resins or polymeric adsorbents, as supplied, as being suitable or appropriately pure for any particular use. Consult your Rohm and Haas technical representative for further information. Acidic and basic regenerant solutions are corrosive and should be handled in a manner that will prevent eye and skin contact. Nitric acid and other strong oxidising agents can cause explosive type reactions when mixed with Ion Exchange resins. Proper design of process equipment to prevent rapid buildup of pressure is necessary if use of an oxidising agent such as nitric acid is contemplated. Before using strong oxidising agents in contact with Ion Exchange Resins, consult sources knowledgeable in the handling of these materials.

Rohm and Haas Company makes no warranties either expressed or implied as to the accuracy or appropriateness of this data and expressly excludes any liability upon Rohm and Haas arising out of its use. We recommend that the prospective users determine for themselves the suitability of Rohm and Haas materials and suggestions for any use prior to their adoption. Suggestions for uses of our products of the inclusion of descriptive material from patents and the citation of specific patents in this publication should not be understood as recommending the use of our products in violation of any patent or as permission or license to use any patents of the Rohm and Haas Company. Material Safety Data Sheets outlining the hazards and handling methods for our products are available on request.

