



DOWEX UPCORE MAC-3

A Weak Acid Cation Exchange Resin Specifically Designed for the UPCORE System

Product	Type	Matrix	Functional group
DOWEX* UPCORE* MAC-3	Weak acid cation	Polyacrylic, macroporous	Carboxylic acid

Guaranteed Sales Specifications		H ⁺ form
Total exchange capacity, min.	eq/l	3.8
	kg/ft ³ as CaCO ₃	83.0
Water content	%	42 - 52
Bead size distribution [†]		
Range, 0.4 mm - 1.2 mm, min.	%	90
>1.2 mm, max (16 mesh)	%	1
<0.35 mm, max (45 mesh)	%	1
Whole beads, min.	%	95

Typical Physical and Chemical Properties		H ⁺ form
Total swelling (H ⁺ → Ca ⁺)	%	15
Particle density	g/ml	1.18
Shipping weight	g/l	750
	lbs/ft ³	47

Recommended Operating Conditions	
Maximum operating temperature	120°C (250°F)
pH range	5-14
Bed depth, min.	1000 mm (3.3 ft)
Pressure drop, design max.	1.5 bar (22 psi)
Pressure drop, max.	2.5 bar (37 psi)
Flow rates:	
Service/fast rinse	5-50 m/h (2-20 gpm/ft ²)
Regeneration/displacement rinse	5-50 m/h (6-20 gpm/ft ²) for H ₂ SO ₄ 6-12 m/h (2.4-4.8 gpm/ft ²) for HCl
Total rinse requirement	3-6 Bed volumes
Regenerant	1-5% HCl, 0.5-0.8% H ₂ SO ₄

[†]For additional particle size information, please refer to the Particle Size Distribution Cross Reference Chart (Form No. 177-01775/CH 171-476-E).

*Trademark of The Dow Chemical Company

DOWEX

Ion Exchange Resins

For more information about DOWEX resins, call Dow Liquid Separations business:

North America 1-800-447-4369
 Latin America (+55) 11-5188-9345
 Europe (+31) 20-691-6268
 Japan (+81) 3-5460-2100
 Australia (+61) 2-9776-3226
<http://www.dow.com/liquidseps>

Typical properties and applications:

DOWEX* UPCORE* MAC-3 macroporous weak acid cation exchange resins contains carboxylic acid functional groups attached to a polyacrylic-divinylbenzene matrix. The particle size is specially chosen for use in the UPCORE packed bed counter-current regeneration system. DOWEX UPCORE MAC-3 resin


efficiently removes hardness associated with alkalinity. When used in combination with DOWEX UPCORE Mono C-600 resin, DOWEX UPCORE MAC-3 resin can be regenerated with effluent acid from the strong acid cation regeneration. This results in highly efficient regeneration of the cation resin pair.

Packaging

25 liter bags or 5 cubic feet fiber drums.

Figure 1. Pressure Drop Data

Temperature = 20° C (68° F)



For other temperatures use:

$$P_T = P_{20^\circ\text{C}} / (0.026 T_{\text{C}} + 0.48), \text{ where } P \equiv \text{bar/m}$$

$$P_T = P_{68^\circ\text{F}} / (0.014 T_{\text{F}} + 0.05), \text{ where } P \equiv \text{psi/ft}$$

Warning: Oxidizing agents such as nitric acid attack organic ion exchange resins under certain conditions. This could lead to anything from slight resin degradation to a violent exothermic reaction (explosion). Before using strong oxidizing agents, consult sources knowledgeable in handling such materials.

Notice: No freedom from any patent owned by Seller or others is to be inferred. Because use conditions and applicable laws may differ from one location to another and may change with time, Customer is responsible for determining whether products and the information in this document are appropriate for Customer's use and for ensuring that Customer's workplace and disposal practices are in compliance with applicable laws and other governmental enactments. Seller assumes no obligation or liability for the information in this document. NO WARRANTIES ARE GIVEN; ALL IMPLIED WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE ARE EXPRESSLY EXCLUDED.

Published September 1998.



*Trademark of The Dow Chemical Company